






DE19616841

Patent number: DE19616841
Publication date: 1996-10-31
Inventor: VANDIEST KAREL (BE); DEPAUW JEAN-MICHEL (BE)
Applicant: GLAVERBEL (BE)
Classification:
- **international:** C03C17/36; C03C17/36; (IPC1-7): C03C17/36;
B32B17/06; G02B1/10
- **european:** C03C17/36
Application number: DE1961016841 19960426
Priority number(s): GB19950008543 19950427

Also published as:

 LU88748 (A)
 JP8304601 (A)
 GB2300133 (A)
 FR2733495 (A1)
 ES2119681 (A1)

more >>

[Report a data error here](#)**Abstract of DE19616841**

A coated substrate comprises a surface carrying a plurality of metal layers formed of silver or silver alloy and layers of a transparent dielectric non-absorbent material. The sequence of layers is: (i) a first layer of transparent dielectric non-absorbent material adjacent the substrate having an optical thickness of between 60 and 75 nm; (ii) a first layer of silver or silver alloy having a geometric thickness of between 9 and 11 nm; (iii) a second layer of transparent dielectric non-absorbent material having an optical thickness of between 135 and 170 nm; (iv) a second layer of silver or silver alloy having a geometric thickness of between 12 and 15 nm; and (v) a third layer of transparent dielectric non-absorbent material having an optical thickness of between 45 and 65 nm. The nature and thicknesses of the coating layers are such that the coated substrate exhibits a luminous transmission TLC greater than 70%, a solar factor F S less than 47%, and a purity of colour in reflection normal to the opposite surface of not more than 12%. The products may be used as glazing panels for buildings or vehicles.

Data supplied from the esp@cenet database - Worldwide